

A method for creating materials with a desired refraction coefficient

A G Ramm

Department of Mathematics
Kansas State University, Manhattan, KS 66506-2602, USA
ramm@math.ksu.edu

Abstract

It is proposed to create materials with a desired refraction coefficient in a bounded domain $D \subset \mathbb{R}^3$ by embedding many small balls with constant refraction coefficients into a given material. The number of small balls per unit volume around every point $x \in D$, i.e., their density distribution, is calculated, as well as the constant refraction coefficients in these balls. Embedding into D small balls with these refraction coefficients according to the calculated density distribution creates in D a material with a desired refraction coefficient.

MSC: 35J10, 74J25, 81U40; PACS 43.20.+g, 62.40.+d, 78.20.-e

Key words: scattering by small inhomogeneities; materials; refraction coefficient; embedding of small inhomogeneities

1 Introduction

In [1]-[3] it was proposed to create material with a desired refraction coefficient by embedding into a given material small particles with suitably chosen boundary impedances. It was proved that any desired refraction coefficient $n^2(x)$, $\Im n^2(x) \geq 0$, can be created in such a way in an arbitrary given bounded domain $D \subset \mathbb{R}^3$. Preparing small particle with a prescribed large boundary impedance may be a technologically challenging problem. By this reason we propose in this paper a new method for creating materials with a desired refraction coefficient. We hope that this method may be easier to implement practically.

This method for creating materials with a desired refraction coefficient $n^2(x)$ consists of embedding into a given material small particles (balls) with a suitably chosen density distribution of the embedded particles and a suitably chosen constant refraction coefficients of each of the embedded particles. No boundary impedances are necessary to use in this method. Therefore, one hopes that the new method may be easier to implement in practice.

The density of the distribution of the embedded particles and their constant refraction coefficients are calculated given the desired refraction coefficient $n^2(x)$ and the refraction coefficient $n_0^2(x)$ of the original material in D .

Let us formulate the problem precisely. Assume that a bounded domain $D \subset \mathbb{R}^3$ is filled with a material with known refraction coefficient $n_0^2(x)$, $\Im n_0^2(x) \geq 0$, $n_0^2(x) = 1$ in $D' := \mathbb{R}^3 \setminus D$, $n_0^2(x)$ is piecewise-continuous. Throughout this paper by piecewise-continuous function we mean a bounded function with the set of discontinuities of Lebesgue measure zero in $\mathbb{R}^3$, and do not repeat this.

The waves satisfy the equation:

$$L_0 u_0 := [\nabla^2 + k^2 n_0^2(x)] u_0 = 0 \quad \text{in } \mathbb{R}^3, \quad k = \text{const} > 0, \quad (1)$$

$$u_0 = e^{ik\alpha \cdot x} + v. \quad (2)$$

Here v is the scattered field, satisfying the radiation condition:

$$v_r - ikv = o(r^{-1}) \quad r := |x| \rightarrow \infty, \quad (3)$$

where $\alpha \in S^2$ is the direction of the incident plane wave, and S^2 is the unit sphere in $\mathbb{R}^3$. It is proved in [1] that this scattering problem under the stated assumptions on $n_0^2(x)$ has a unique solution, and the function $G(x, y)$, satisfying the equation

$$L_0 G(x, y) = -\delta(x - y) \quad \text{in } \mathbb{R}^3, \quad (4)$$

and the radiation condition (3), does exist and is unique.

One can write

$$L_0 = \nabla^2 + k^2 - q_0(x),$$

where

$$q_0(x) := q_0(x, k) := k^2 - k^2 n_0^2(x), \quad q_0(x) = 0 \quad x \in D'. \quad (5)$$

Let $n^2(x)$ be a desired refraction coefficient in D . We assume that $n^2(x)$ is piecewise-continuous, $\Im n^2(x) \geq 0$, and $n^2(x) = 1$, $x \in D'$.

We wish to create material with the refraction coefficient $n^2(x)$ in D by embedding into D many small non-intersecting balls B_m , $1 \leq m \leq M$, of radius a , centered at the points $x_m \in D$, with constant refraction coefficients n_m^2 in B_m .

Smallness of the particles means that $ka \ll 1$.

Let $\Delta \subset D$ be any subdomain of D . We assume that the number of small particles, embedded in Δ , is given by the formula:

$$\mathcal{N}(\Delta) := \sum_{x_m \in \Delta} 1 = V_a^{-1} \int_{\Delta} N(x) dx [1 + o(1)] \quad a \rightarrow 0, \quad (6)$$

where $N(x) \geq 0$ is a piecewise-continuous function in D , and

$$V_a := 4\pi a^3/3$$

is the volume of a ball of radius a .

Formula (6) gives the density distribution of the centers of the embedded small balls in D . The total number of these balls tends to infinity as $O(V_a^{-1}) = O(a^{-3})$ when $a \rightarrow 0$.

We assume that the total volume $V(D)$ of the embedded particles (balls) is not greater than $|D|$, where $|D|$ is the volume of D , i.e.,

$$V(D) = V_a \mathcal{N}(D) = \int_D N(x) dx [1 + o(1)] \leq |D|, \quad a \rightarrow 0.$$

This means physically that although $N(x)$ can be large in some subdomains of D , its average over D is not greater than 1.

The scattering problem in the case of the embedded into D particles is:

$$(L_0 + k^2 \sum_{m=1}^M n_m^2 \chi_m) U = 0 \quad \text{in } \mathbb{R}^3, \quad (7)$$

where χ_m is the characteristic function of the ball B_m , i.e., $\chi_m = 1$ in B_m , $\chi_m = 0$ in $B'_m := \mathbb{R}^3 \setminus B_m$, and

$$U = u_0 + V, \quad (8)$$

where V satisfies the radiation condition (3), u_0 solves the scattering problem in the absence of the embedded particles, i.e., when $M = 0$, and

$$n_m^2 = \nu^2(x_m).$$

Here $\nu^2(x)$ is some piecewise-continuous function in D , $\Im \nu^2(x) \geq 0$.

The solution $U(x) = U_a(x)$ to problem (7)-(8) depends on the parameter a , and the number M of the embedded particles depends also on a ,

$$M = O(V_a^{-1}) = O(a^{-3}),$$

so $M \rightarrow \infty$ at a prescribed rate as $a \rightarrow 0$. We are interested in the limiting behavior of $U(x) = U_a(x)$ as $a \rightarrow 0$. Our basic result, Theorem 1, below, says that the limit

$$\lim_{a \rightarrow 0} U_a(x) := u_e(x), \quad (9)$$

does exist and satisfies the integral equation (17) in Theorem 1.

From (7)-(8) one gets

$$U(x) = u_0(x) + k^2 \sum_{m=1}^M n_m^2 \int_{B_m} G(x, y) U(y) dy. \quad (10)$$

This integral equation we rewrite as

$$U(x) = u_0(x) + k^2 \sum_{m=1}^M n_m^2 \int_{B_m} G(x, y) dy U(x_m) [1 + o(1)] \quad a \rightarrow 0. \quad (11)$$

Here the continuity of U in B_m , $1 \leq m \leq M$, was used. This continuity implies

$$U(y) = U(x_m)[1 + o(1)] \quad a \rightarrow 0; \quad y \in B_m.$$

The function U is twice differentiable in $\mathbb{R}^3$, as follows from (11), so it is continuous in D .

We need three lemmas.

Lemma 1. *The following relations hold:*

$$\lim_{|x-y| \rightarrow 0} |x-y|G(x,y) = \frac{1}{4\pi}, \quad (12)$$

$$\sup_{|x-y| \geq 0} |x-y||G(x,y)| \leq c. \quad (13)$$

By $c > 0$ we denote various estimation constants.

Proof of Lemma 1 is given in Section 2.

Lemma 2. *The following relations hold:*

$$\begin{aligned} \int_{|y-x_m| \leq a} |x-y|^{-1} dy &= V_a |x-x_m|^{-1}, \quad |x-x_m| \geq a, \\ \int_{|y-x_m| \leq a} |x-y|^{-1} dy &= 2\pi \left(a^2 - \frac{|x-x_m|^2}{3} \right), \quad |x-x_m| \leq a. \end{aligned} \quad (14)$$

Proof of Lemma 2 consists of a direct routine calculation and is therefore omitted. The result of Lemma 2 is known from the potential theory.

Lemma 3. *If f is piecewise-continuous in D and the points x_m are distributed in D by formula (6), then the following limit exists:*

$$\lim_{a \rightarrow 0} V_a \sum_{m=1}^M f(x_m) = \int_D f(x) N(x) dx, \quad (15)$$

where $N(x)$ is defined in (6).

This Lemma is proved in [1].

One has:

$$\int_{B_m} G(x,y) dy = V_a G(x, x_m) [1 + o(1)], \quad a \rightarrow 0. \quad (16)$$

From (11), (16) and (15) our basic result follows:

Theorem 1. *There exists the limit (9) and*

$$u_e(x) = u_0(x) + k^2 \int_D G(x,y) N(y) \nu^2(y) u_e(y) dy. \quad (17)$$

Physically the limiting field u_e is interpreted as the effective (self-consistent) field in D .

Corollary 1. The functions $U(x)$ and $u_e(x)$ are twice differentiable in $\mathbb{R}^3$. The function $u_e(x)$ solves the equation:

$$Lu_e(x) = 0, \quad L := L_0 + k^2 N(x) \nu^2(x), \quad (18)$$

so

$$n^2(x) = n_0^2(x) + N(x) \nu^2(x). \quad (19)$$

To prove this Corollary one applies the operator L_0 to equation (17) and uses equation (4).

Conclusion: *To construct a material with a desired refraction coefficient $n^2(x)$ one embeds small balls with radius a , centered at the points x_m , $1 \leq m \leq M$, distributed by formula (6), and chooses $N(x)$ and $\nu^2(x)$ so that relation (19) holds.*

The choice of $N(x)$ and $\nu^2(x)$ is therefore non-unique, because the relation (19) can be satisfied by infinitely many ways. For example, one may fix $N(x) > 0$ in D and then choose

$$\nu^2(x) = \frac{n^2(x) - n_0^2(x)}{N(x)}.$$

If $n^2(x) = 0$ in a subdomain $\Delta \subset D$, then one can take $N(x) = 0$ in Δ .

In Section 2 proof of Lemma 1 is given.

2 Proofs

Proof of Lemma 1. We start with the equation:

$$G(x, y) = g(x, y) - \int_D g(x, z) q_0(z) G(z, y) dz := g - TG, \quad (20)$$

where q_0 is defined in (5), and

$$g(x, y) = \frac{e^{ik|x-y|}}{4\pi|x-y|}. \quad (21)$$

Equation (20) is of Fredholm-type in the space X of functions $\psi(x, y)$ of the form $\psi(x, y) = \frac{\phi(x, y)}{|x-y|}$, where $\phi(x, y)$ is a continuous function of its arguments, and the norm in X is defined as $\|\psi\| = \sup_{x, y \in \mathbb{R}^3} (|x-y| |\psi(x, y)|)$.

We have $\|g\| = \frac{1}{4\pi}$. The homogeneous equation (20) has only the trivial solution (see [1]), so the operator $(I + T)^{-1}$ is bounded in X . Therefore, $\|G\| \leq c\|g\| = \frac{c}{4\pi}$. This implies estimate (13).

To prove (12), let us multiply (20) by $|x-y|$ and let $|x-y| \rightarrow 0$. One has $\lim_{|x-y| \rightarrow 0} g = \frac{1}{4\pi}$. The integral TG is bounded for all $x, y \in D$, so $\lim_{|x-y| \rightarrow 0} (|x-y|TG) = 0$. Thus, relation (12) follows.

Lemma 1 is proved. $\square$

References

- [1] A.G.Ramm, Many-body wave scattering by small bodies and applications, J. Math. Phys., 48, N10, (2007), 103511.
- [2] A.G.Ramm, Distribution of particles which produces a "smart" material, Jour. Stat. Phys., 127, N5, (2007), 915-934.
- [3] A.G.Ramm, Wave scattering by many small particles embedded in a medium, Phys. Lett. A, 372/17, (2008), 3064-3070.